

硬さ換算表

ブリネル HB	ロックウェル HRC	ショア HS	引張強さ kgf/mm ²
363	39.1	52	124
352	37.9	51	120
341	36.6	50	115
331	35.5	48	112
321	34.3	47	108
311	33.1	46	105
302	32.1	45	103
293	30.9	43	99
285	29.9	42	97
277	28.8	41	94
269	27.6	40	91
262	26.6	39	89
255	25.4	38	86
248	24.2	37	84
241	22.8	36	82
235	21.7	35	80
229	20.5	34	78
223	18.8	—	76
217	17.5	33	74
212	16.0	—	72
207	15.2	32	70
201	13.8	31	69
197	12.7	30	67
192	11.5	29	65
187	10.0	—	63
183	9.0	28	63
179	8.0	27	61
174	6.4	—	60
170	5.4	26	58
167	4.4	—	58