

硬 さ 換 算 表

	ブリネル HB	ロックウェル HRC	シヨア HS	引張強さ kg
	363	39.1	52	124
	352	37.9	51	120
	341	36.6	50	115
	331	35.5	48	112
SNCM439 [Ⓜ]	321	34.3	47	108
SCM440 [Ⓜ]	311	33.1	46	105
	302	32.1	45	103
SCM435 [Ⓜ]	293	30.9	43	99
	285	29.9	42	97
SNC631 [Ⓜ]	277	28.8	41	94
	269	27.6	40	91
	262	26.6	39	89
	255	25.4	38	86
	248	24.2	37	84
	241	22.8	36	82
S45C [Ⓜ]	235	21.7	35	80
	229	20.5	34	78
	223	18.8	—	76
	217	17.5	33	74
	212	16.0	—	72
	207	15.2	32	70
	201	13.8	31	69
S45C [Ⓝ]	197	12.7	30	67
	192	11.5	29	65
	187	10.0	—	63
	183	9.0	28	63
SUS304ST	179	8.0	27	61
SUS403 [Ⓜ]	174	6.4	—	60
	170	5.4	26	58
	167	4.4	—	58

[J I S 参考値]